


**CONVEYOR AND PROCESS BELTS**
**TECHNICAL DATA SHEET**
**CODE NA-223**
**TYPE**
**SILON 60 NA**
**COMPOSITION**

<b>Conveying side</b>	material	Non-woven Polyester (PET)			
	thickness	---	mm	---	in
	cover finish	rough			
	colour	green			
	coeff. of friction	LF			
<b>Textile carcass</b>	material	Polyester (PET)			
	no. of plies	1			
	type of weft	flexible			
<b>Driving side</b>	material	Non-woven Polyester (PET)			
	thickness	---	mm	---	in
	cover finish	rough			
	colour	green			


**TECHNICAL SPECIFICATIONS**

Total thickness		5,5 mm	0,22 in.
Weight		3,4 kg/m <sup>2</sup>	0,69 lbs./sq.ft
Trazione all'1% d'allungamento		10 N/mm	57,1 lbs./in.
Max. admitt. load		10 N/mm	57,1 lbs./in.
Temperature resistance <sup>(1)</sup>	min.	-20 °C	-4 °F
	max.	+120 °C	248 °F

<sup>(1)</sup> use of the belt with limit values may reduce its life

**Minimum pulley diameter**

■ knife edge		no	
■ bending pulley	100 mm		3,94 in.
■ counter-bending pulley	125 mm		4,92 in.

the above mentioned values depend on the type of CHIORINO joint recommended

**Coefficient of friction of driving surface**

■ raw steel sheet	0,20 [-]
■ laminated plastic/wood	0,25 [-]
■ steel roller	0,20 [-]
■ rubberized roller	0,30 [-]

Max. production width	2000 mm	79 in.
-----------------------	---------	--------

**JOINTING METHODS**

See jointing data sheet

**NOTES**

Due to the product structure, these data represents a guideline only and can be changed without notice.

**FEATURES**

FDA conformity	no
USDA conformity	no
HACCP conformity (CEE 72/2002)	no
Flame Retardant (EN20340-ISO340)	no
Humidity influence	no
Suitable to metal detector	yes
Permanent antistatic dynamically (UNI EN 1718)	no
Static conductivity (ISO 284)	no
Conveying on skid bed	yes
Conveying on rollers	yes
Conveying on skid bed on top and return	yes
Troughed conveying	yes
Swan neck conveying	no
Inclined conveying	no
Accumulators belts	yes
Curved conveyor	no
Chemical resistances (see chart of chemical resistances)	11

**SUITABLE FOR**

 Packaging and confectionary  
 Paper industry  
 Wood industry  
 Magnetic conveying  
 In-house handling

Issue: 10-03-2003

Date last modified: 29-05-2007

**DISCLAIMER**

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.

CODE NA-223

TYPE

**SILON 60 NA**

• Recommended jointing procedure

SKIVED JOINT '1'



Check our general catalogue to get further info on CHIORINO jointing methods.


• Skiving instructions

Skiver	Belt thickness mm	Length mm	Straight/ diagonal cut	Cam/ wedge number	Pulley				Top cover			
					T mm	B mm	Thickness adjustment	End stop switch of working plate	T mm	B mm	Thickness adjustment	End stop switch of working plate
<b>B600 A</b>	5,4	60	Diagonal	1-10	6	15	17,85	--	--	--	--	--
<b>B300 SA</b>	---	---	---	---	---	---	---	---	---	---	---	---

• Guide to the use of adhesives

Pour the **I hardener** with the **R cement** (pot-life 2 hours).  
 Apply a thin layer of above mix on both splices.  
 Let dry for 5 minutes, then match the belt ends, paying attention to align properly.  
 Press according to the instructions shown.  
 To ensure best joint life it is advisable not to run or tension the belt for 24 hours.  
 Kit: **SINTECOL**.

• Layout of components



Press settings	
Upper platen temperature	100 °C
Lower platen temperature	100 °C
Curing time in press	20 min.
Driving torque	30 N/m
Cooling time: the belt shall be removed from the press only when room temperature is reached.	

• Notes

Issue: 30-09-2005

Date last modified: 04-05-2007

**DISCLAIMER**

The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.